



WINDOWS&DOORS

FAST-DRYING WATERBORNE ALKYD ENAMEL



- For Windows and Doors
- Protects wood from atmospheric exposure
- Good hiding power
- Withstands temperature fluctuations

DESCRIPTION:

Fast-drying, waterborne alkyd enamel that forms a durable semi-matt coating resistant to atmospheric precipitation. It provides excellent adhesion to wood and primed metal, ensuring a long-lasting and even finish. Easy to apply and suitable for use both indoors and outdoors.

FIELD OF APPLICATION:

Intended for painting wooden and primed metal surfaces such as window frames, sills, doors, casings, and other elements used both outdoors and indoors.

<u>TECHNICAL PARAMETERS:</u>	
<u>Colour:</u>	White (A base), which may be tinted in to light shades. C base is used only for tinting in to deep shades. Tinting is performed by RILAKOLOR system.
<u>Gloss:</u>	semi-matt.
<u>Drying time at 20°C temperature:</u>	6 hours
<u>Solids contents (by weight), %</u>	54,0±3,0 (base A) 36,0±3,0 (base C)
<u>Consumption:</u>	7÷10 m ² /l
<u>Solvent:</u>	Water
<u>Tools used for painting:</u>	Brush, roller, spray gun or airless spray (nozzle diameter 0,011" – 0,017").
<u>Storage period:</u>	36 months in tightly closed manufacturer's container at the temperature between +5°C and +30°C.
<u>Packaging::</u>	0.9 l; 2.7 l

APPLICATION:

PREPARATION OF PAINT FOR WORK:

The product is ready to use and does not require dilution. Stir thoroughly before use. If necessary, dilute with water up to 0–15% by volume to reach working viscosity.



PREPARATION OF SURFACE:

Before painting, surfaces must be dry and free of grease (oil stains), flaking paint, contaminants, and rust. Previously painted glossy surfaces must be sanded to remove the gloss. Old wood surfaces should be disinfected with AKVASEPT solution prior to coating.

PRIMING OF SURFACE:

or untreated exterior wooden surfaces, it is recommended to use TEKSTURDEKOR clear wood preservative as a primer. For steel surfaces exposed to the weather, use primers such as GF-021, NOVAKOR, NEOSPRINT PRIMER, or RIATOP PRIMER. For aluminum or galvanized metal, use VL-02 or NEOSPRINT PRIMER.

PAINTING:

Apply 1–2 coats using a brush, roller, spray gun, or airless spraying equipment (recommended nozzle size: 0.011"–0.017").

Apply at ambient and substrate temperatures not below +10°C and relative air humidity not exceeding 70%. DRYING TIME (per coat): +20°C: 6 hours, +10°C: 8 hours. Recoating interval: at +20°C: min. 8 hours, at +10°C: min. 12 hours.

CLEANING OF TOOLS:

Use water for cleaning of tools.

LABOUR AND ENVIRONMENTAL PROTECTION:

Keep out of reach of children. Avoid breathing dust/fume/gas/mist/vapours/spray. IF SWALLOWED: Call a POISON CENTER or doctor/physician if you feel unwell. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

More detailed information is provided on the label and in the safety data sheet, which is available upon request.



0.9l, 2.7l



7÷10 m²/l



6 h



RILAKOLOR
(A, C BASE)



The information in this document is given to the best of our knowledge, based on laboratory testing and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, therefore we cannot guarantee anything but the quality of the product itself in accord with applicable our quality control procedures. We reserve the right to change the given data without further notice. The new information and technical specifications you can find on www.rilak.lv Users should always consult RILAK for specific guidance on the general suitability of this product for their needs and specific application practices.